

DEVELOPMENT OF POLYETHERSULFONE–POLY
VINYLIDENEFLUORIDE (PES-PVDF) THIN FILM COMPOSITE
MEMBRANE FOR CO₂/N₂ GAS SEPARATION

MOHAMAD HADI BIN TAIRIN

DEGREE OF BACHELOR OF CHEMICAL ENGINEERING

UNIVERSITI MALAYSIA PAHANG

DEVELOPMENT OF POLYETHERSULFONE–POLY VINYLIDENEFLUORIDE
(PES-PVDF) THIN FILM COMPOSITE MEMBRANE FOR CO₂/N₂ GAS
SEPARATION

MOHAMAD HADI BIN TAIRIN

A thesis submitted in fulfillment
of the requirements for the award of the Degree of
Bachelor of Chemical Engineering (Gas Technology)

Faculty of Chemical & Natural Resources Engineering
Universiti Malaysia Pahang

FEBRUARY 2013

SUPERVISOR DECLARATION

“I/we hereby declare that I/we have read this thesis and in my/our opinion this thesis has fulfilled the qualities and requirements for the award of Degree of Bachelor of Chemical Engineering (GasTechnology)”

Signature :

Name of Supervisor I : Dr. Sunarti Bt Abdul Rahman

Position : URP Supervisor

Date : 18 February 2013

STUDENT DECLARATION

I declare that this thesis entitled “Development of Polyethersulfone–Poly Vinylidene fluoride (PES-PVDF) Thin Film Composite Membrane for CO₂/N₂ Gas Separation” is the result of my own research except as cited in references. The thesis has not been accepted for any degree and is not concurrently submitted in candidature of any other degree.”

Signature :

Name : Mohamad Hadi Bin Tairin

Date : 18 February 2013

*Special dedications to my mum and dad that always inspire, love and stand beside me,
and to my beloved friend.*

Thank you for all your love, care and support.

ACKNOWLEDGEMENTS

Bismillahirrahmanirrahim and Alhamdulillah. Praise to God for His help and guidance that I finally able to complete this Undergraduate Research Project.

I would like to take this opportunity to express my sincere appreciation to all those people and organizations who contributed to this study. Firstly, thousands of thanks and appreciation goes to my supervisor, Dr. Sunarti Bt. Abdul Rahman, for her guidance, support, motivation, enthusiasm and willingness to teach and share her experience throughout this research project as well as her academic experience, have been invaluable to me.

I also gratefully acknowledge to Universiti Malaysia Pahang (UMP) for giving me the opportunity to take this degree course. The technical staffs of FKKSa especially Mr. Abdul Razak Abdul Hamid, Mr. Mohamad Zaki Bin Sahad, Mr. Mohd Masri Abdul Razak and Mr. Mahadhir Bin Muhammad also deserved special thanks for their assistance in supplying a good ideas, materials, apparatus, equipment, opinions and lend their hands during the research in progressing. I would like to apply most of forgiveness and apologize on my weakness and my mistake whether deliberately or accidentally to all people that involved in this thesis.

Last but not the least, I would like to express my gratitude to my parents, my family, my friends and those who have directly or indirectly assisted me in the preparation of this thesis. I owe everything to them. Besides that, several people have knowingly and unknowingly helped me in the successful completion of this thesis.

TABLE OF CONTENT

CHAPTER	TITLE	PAGE
	SUPERVISOR DECLARATION	iii
	STUDENT DECLARATION	viii
	DEDICATION	ix
	ACKNOWLEDGEMENTS	x
	TABLE OF CONTENTS	xii
	LIST OF TABLES	xvii
	LIST OF FIGURES	xviii
	LIST OF ABBREVIATIONS	xx
	LIST OF SYMBOLS	xxi
	LIST OF APPENDICES	xxii
	ABSTRAK	iv
	ABSTRACT	v

1	INTRODUCTION AND GENERAL INFORMATION	
1.1	Background of Study	1
1.2	Problem Statement	2
1.3	Research Objectives	3
1.4	Scopes of Study	3
1.5	Rational & Significance	3
2	LITERATURE REVIEW	
2.1	Background of the membrane	5
2.1.1	Definition	5
2.1.2	Modules of Membrane	6
2.1.2.1	Spiral-Wound Modules	6
2.1.2.2	Hollow-Fiber Module	7
2.1.2.3	Plate & Frame Module	8
2.1.3	Membrane process, type, material and application	9
2.1.4	Structure of Membrane	10
2.1.4.1	Symmetric Membrane	10
2.1.4.2	Asymmetric Membrane	10
2.1.5	Advantages of membrane	11
2.1.6	Disadvantages of membrane	12
2.1.7	Gas permeation in a membrane	13
2.1.8	Mechanism of Membrane Separation Process	14
2.1.8.1	Pressure Driven	14

2.2	Membrane gas separation	16
2.2.1	History	16
2.2.2	Application of membrane gas separation	16
2.2.3	Characteristics of Membrane for Gas Separation	18
2.2.4	Types of membrane gas separation	18
2.2.4.1	Polymer	18
2.2.4.2	Solubility-Controlled Membranes	19
2.2.4.3	Mixed Matrix Membranes	19
2.2.4.4	Zeolite Membranes	20
2.2.5	Mechanism of membrane gas separation	20
2.2.6	Factors affecting membrane performance	21
2.2.6.1	Feed Composition and Concentration	21
2.2.6.2	Feed and Permeate Pressure	22
2.2.7	Relation between permeability and selectivity of gas separation	22
2.3	TFC membrane for gas separation	23
2.3.1	Application TFC membrane for gas separation	24
2.3.2	Advantages TFC membrane for gas separation	24
2.3.3	Disadvantages TFC membrane for gas separation	24
2.3.4	PES-PVDF TFC membrane to CO ₂ /N ₂ separation	25
2.3.4.1	TFC Membrane preparation	25
2.3.4.2	Dope solution preparation	25
2.3.4.3	Membrane fabrication (casting) process	27
2.3.4.4	Membrane dip-coating (interfacial polymerization)	27
2.3.5	Effect to environment	28

3	RESEARCH METHODOLOGY	
3.0	Membrane preparation	30
3.1	Material	31
3.2	Preparation for dope solution	33
3.2.1	Dope solution for PVDF and PES	33
3.3	Membrane casting process	33
3.4	Membrane dip-coating	34
3.5	Membrane gas permeation test	35
3.6	Membrane characterization	35
4	RESULT AND DISCUSSION	
4.1	Effect of various concentration of coating solution on the membrane gas permeation	37
4.1.1	Effect of different pressure and different concentration of coating solution on the gas permeance for CO ₂ gas.	38
4.1.2	Effect of different pressure and different concentration of coating solution on the gas permeance for N ₂ gas.	39
4.2	PES/PVDF for TFC membrane characterizations	44
4.2.1	Identification of functional group in the PES/PVDF for TFC membrane	44
4.2.2	Effect of different concentration coating solution on membrane morphology	49
5	CONCLUSION & RECOMENDATION	
5.1	Conclusion	53

5.2	Recommendation	54
	REFERENCES	55
	APPENDICES	58

LIST OF TABLES

Table No.	Title	Page
2.1	Membrane characterization	9
2.2	Application of Membrane for Gas Separation	17
2.3	Polymer in gas separation	19
2.4	Dope solution formula after titration	26
2.5	Composition of casting solution for PES/PVDF blend membrane preparation	26
3.1	Physical and chemical properties for N-Methyl Pyrrolidone (NMP)	32
3.2	Physical and chemical properties for Poly Vinylidene Fluoride (PVDF)	32
4.1	CO ₂ Gas permeance (GPU)	38
4.2	N ₂ Gas permeance (GPU)	40
4.3	The relationship between the gas permeance and the selectivity	42
4.4	Sulfones and Sulfonates Group for aliphatic bands	45
4.5	Sulfones and Sulfonates Group for aromatic bands	45
4.6	Amines Group	47

LIST OF FIGURES

Figure No.	Title	Page
2.1	Spiral-Wound Modules	7
2.2	Hollow-Fiber Module	8
2.3	Plate & Frame Modules	9
2.4	Gas permeation membrane process	13
3.1	Membrane preparation for overall flow process	31
4.1	CO ₂ gas permeance (GPU) VS. Pressure (bar)	39
4.2	N ₂ gas permeance (GPU) VS. Pressure (bar)	41
4.3	Gas Permeance vs. Selectivity	43
4.4 (a)	PVDF (15%) coated by PES (18%) for aliphatic bands	45
4.4 (b)	PVDF (15%) coated by PES (23%) for aliphatic bands	46
4.4 (c)	PVDF (15%) coated by PES (28%) for aliphatic bands	46
4.5 (a)	PVDF (15%) coated by PES (18%) for amines group	47
4.5 (b)	PVDF (15%) coated by PES (23%) for amines group	48
4.5 (c)	PVDF (15%) coated by PES (28%) for amines group	48
4.6 (a)	PVDF coated by 18% PES at magnification 300X	50

4.6 (b)	PVDF coated by 18% PES at magnification 1000X	50
4.7 (a)	PVDF coated by 23 % PES at magnification 300X	51
4.7 (b)	PVDF coated by 23 % PES at magnification 779X	51
4.7 (c)	PVDF coated by 23 % PES at magnification 1000X	51
4.8 (a)	PVDF coated by 28 % PES at magnification 300X	52
4.8 (b)	PVDF coated by 28 % PES at magnification t 493X	52
4.8 (c)	PVDF coated by 28 % PES at magnification 1000X	52
4.8 (d)	PVDF coated by 28 % PES at magnification 1000X	52

LIST OF ABBREVIATIONS

PES	-	Polyethersulfone
PVDF	-	Poly (vinylidene fluoride)
PEG	-	Polyethylene Glycol
PS	-	Polysulfone
PP	-	Polypropylene
SEM	-	Scanning Electron Microscope
FTIR	-	Fourier Transform Infrared
N ₂	-	Nitrogen
CO ₂	-	Carbon dioxide
NMP	-	N-methyl-2-pyrrolidone
TFC	-	Thin Film Composite
UF	-	Ultrafiltration
MF	-	Microfiltration
RO	-	Reverse Osmosis

LIST OF SYMBOL

P_i	-	Permeability for Gas component
Q	-	Volumetric Gas Flowrate
A	-	Effectiveness Membrane Area
ΔP	-	Pressure in System
l	-	Membrane Thickness
α	-	Selectivity
$^{\circ}\text{C}$	-	Degree Celcius
K	-	Kelvin

LIST OF APPENDICES

Appendix	Title	Page
A	Volumetric Gas flowrate (Q) of CO ₂ gas permeate through the TFC membrane	58
B	Volumetric Gas flowrate (Q) of N ₂ gas permeate through the TFC membrane.	59
C	CO ₂ Gas Permeance at Different Pressure	60
D	N ₂ Gas Permeance at Different Pressure	61
E	Polyethersulfone in gel form	62
F	Dope Solution of PVDF and PES	62
G	Thin Film Composite (TFC) membrane	62
H	Gas Permeation Rig	63

**PEMBENTUKAN POLYETHERSULFONE–POLY VINYLIDENEFLUORIDE
(PES-PVDF) BAGI KOMPOSIT FILEM NIPIS (TFC) UNTUK PEMISAHAN
GAS KARBON DIOKSIDA (CO₂) DAN GAS NITROGEN (N₂)**

ABSTRAK

Tujuan utama kajian ini adalah untuk menghasilkan komposit filem nipis (TFC) dengan menggunakan polietersulfon-poli (vinylidene fluoride) (PES PVDF) untuk pemisahan gas CO₂/N₂. Tujuan lain adalah untuk mengkaji segmen pada Poli (vinylidene fluoride) (PVDF) sebagai lapisan sokongan pada membran untuk meningkatkan kadar kebolehtelapan dan keterpilihan untuk pemisahan gas. Pertama, membran sokongan mestilah terdiri daripada vinylidene fluoride poli (PVDF), N-metil-2-pyrrolidone (NMP) dan sedikit peratusan air. Larutan polymer dan pelarut yang merupakan larutan bagi sokongan untuk membran TFC telah disediakan dengan menggunakan kaedah konvensional dan elektrik pemanasan. Larutan untuk lapisan atas untuk kajian ini terdiri daripada PES, N-metil-2-pyrrolidone (NMP) dan air atau heksana. Kemudian, larutan PES akan disalut pada PVDF membran yang telah siap dituang dan diratakan dengan menggunakan rod kaca. Lapisan untuk salutan dilaksanakan di atas plat kaca. Ujian penyerapan dijalankan dengan menggunakan gas karbon dioksida (CO₂) tulen dan gas nitrogen (N₂) tulen melalui TFC membran untuk melihat kebolehtelapan dan pemilihan gas masing-masing. Prestasi membran ini diukur berdasarkan kepada kebolehtelapan dan pemilihan untuk pemisahan gas CO₂/N₂. PVDF telah bertindak sebagai polimer asas, manakala N-metil Pyrrolidone (NMP) telah digunakan sebagai pelarut. TFC membran dianalisis menggunakan kaedah Mikroskop Imbasan Elektron (SEM) dan Sinaran inframerah transformasi Fourier (FTIR) untuk menentukan struktur dan kumpulan berfungsi yang wujud dalam membran. Gabungan antara liang-liang pada sokongan membran dan kepekatan larutan penyalut akan mencapai tahap terbaik dari segi kebolehpilihan dan kebolehtelapan masing-masing. Gas karbon dioksida (CO₂) perlu dipisahkan daripada gas bahan api untuk mengurangkan pelepasan gas karbon dioksida (CO₂) yang boleh menyebabkan isu-isu alam sekitar seperti pemanasan global, perubahan iklim dan kesan rumah hijau.

**DEVELOPMENT OF POLYETHERSULFONE–POLY
VINYLIDENEFLUORIDE (PES-PVDF) THIN FILM COMPOSITE
MEMBRANE FOR CO₂/N₂ GAS SEPARATION**

ABSTRACT

The main purpose for this study is to produce thin film composite (TFC) by using Polyethersulfone –poly (vinylidene fluoride) (PES–PVDF) for CO₂/N₂ gas separation. The other purpose is to investigate the segment of Poly (vinylidene fluoride) (PVDF) as the membrane support to improve the rate of permselectivity for gas separation. First, the support membrane was development consist of poly vinylidene fluoride (PVDF), N-methyl-2-pyrrolidone (NMP) and water. The dope solution which is solution for support membrane for TFC membrane was prepared by using conventional and electrical heating method. The coating solution developed in this research consists of PES, N-methyl-2-pyrrolidone (NMP) and water or hexane. Then, the PES solution was coated on the PVDF casted by using glass rod. The coating layer was performed on the glass plate. Permeation test was carried out by testing pure of CO₂ and N₂ through the TFC membrane to see the permeability and selectivity. We measure the performance of this membrane based on terms of permeability and selectivity for the CO₂/N₂ gas separation. PVDF was employed as a base polymer, while N-methyl pyrrolidone (NMP) was used as a solvent. The prepared TFC membrane was characterized using Scanning Electron Microscope (SEM) and Fourier Transform Infrared Radiation (FTIR) method to determine the structure and functional group of our membrane. The combination of support porosity and concentration of coating solution could lead to achieve the optimum of selectivity and permeability respectively. The CO₂ should be separated from the fuel gas to reduce the CO₂ emission that can cause of environmental issues like global warming, climate change and greenhouse effect.

CHAPTER 1

INTRODUCTION

1.1 BACKGROUND OF STUDY

As energy costs rise, membrane technology for separating gases is likely to play an increasingly important role in reducing the environmental impact and costs of industrial processes. In addition, gas separation membrane units are smaller than other types of plants, like amine stripping plants, and therefore have relatively small footprints. A small footprint is important in environments such as offshore gas-processing platforms. Currently, gas separation membranes are most widely used in industry for CO₂ and water removal from natural gas. At the moment, the most widely used membrane materials for gas separation are polymers. Composite membrane including thin film composite (TFC) can be prepared by using dry and wet process. For example, in the dry process, there are the vapor depositions, the plasma-initiated polymerization and the radiation polymerization methods. In the wet process, there are polymer coating and spreading on water surface. Currently, among the types of support used for dip-coating are mostly Polysulfone (PSF) or Polyethersulfone (PES). However,

Polypropylene (PP) and polyvinylidene fluoride (PVDF) are very attractive materials as a hydrophobic support for forming a TFC membrane due to its high durability and resistance to chemicals, pH variations, and a substantially wide range of solvents. The economics of a gas separation membrane process is largely determined by the membrane's transport properties, which are permeability and selectivity for a specific gas in a mixture. Ideally, membranes should exhibit high selectivity and high permeability. For most membranes, however, as selectivity increases, permeability decreases, and vice versa.

1.2 PROBLEM STATEMENT

Membrane gas separation is a dynamic and rapidly growing field due to the high selectivity and fluxes achievable by membranes, low energy requirements, and simple, easy to operate modules. From the previous study, the formation of TFC membrane over PVDF substrate have a some weakness on the membrane characterization, strength and effectiveness of Polyethersulfone (PES) segment, and the rate of permeability and selectivity of the selected composite membrane Polyethersulfone–Poly (vinylidene fluoride) (PES-PVDF) for mixed CO₂/N₂ at varying pressure and feed concentration at ambient temperature. Now, we introduce method to improved permeability and selectivity for CO₂/N₂ gas separation.

1.3 RESEARCH OBJECTIVES

The first objective of this study are:to develop Poly-vinylidene fluoride (PVDF) membrane. The second objective are to produce thin film composite (TFC) by using Polyethersulfone–Poly (vinylidene fluoride) (PES–PVDF) polymer as membrane support for CO₂/N₂ separation. The last objectives of our research are to study the characteristic and performances of TFC membrane.

1.4 SCOPES OF STUDY

In order to achieve the objectives, the following scopes have been identified:

- i. Study on production of TFC membrane preparation.
- ii. Study on performances of TFC membrane for CO₂/N₂ gas separation using single gas permeation rig.
- iii. Study on characteristics of the TFC membrane by using SEM and FTIR.

1.5 RATIONALE & SIGNIFICANCE

The rational of this study is to get the potential of (PES–PVDF) as basic polymers for TFC membrane development. The key problems are related to the selectivity/permeability ratio and the stability under process conditions. For such special polymers, which may have high cost, the manufacturing of thin film composite membranes and the processing of the polymer preparation from dope solutions, should

be possible. Besides that, the production of TFC can be increased. Hence, it can give the beneficial to the company. In addition to the power generation industry, there have a number of different point sources which produce large CO_2 emissions. CO_2/N_2 separation membranes can be used to create oxygen enriched air, which can be used in combustion, to get concentrated CO_2 flue gases.